



PRODUCT NAME	SealTite PRO Open Cell	SealTite PRO High Yield	SealTite PRO No Mix	SealTite PRO OCX	SealTite PRO No Trim 21	SealTite PRO XTR	SealTite PRO HFO
Set Weight, Lbs	975	975	960	1000	975	960	1000
Evaluation Report	UES ER-624 CCRR-1121	UES ER-623 CCRR-0298	UES ER-616 CCRR-0293	UES ER-615	UES ER-618	UES ER-906	UES ER-720
Ignition Barriers	DC315 Plus XD BMS IC FS-IB IB 4	DC315 Plus XD BMS IC FS-IB IB 4	DC315 Plus XD Plus ThB FS-IB	Not Required	DC315	DC315 Plus XD BMS IC FS-IB IB 4	Not Required
Thermal Barriers	DC315 Plus ThB BMS TS	DC315 Plus ThB BMS TC	DC315 Plus ThB	DC315 60-60A	DC315	DC315 Plus ThB Flame Seal	DC315 Plus ThB 60-60A F10E

## VISCOSITY CURVES

Temperature (°F)	SealTite PRO Open Cell	SealTite PRO High Yield	SealTite PRO No Mix	SealTite PRO OCX	SealTite PRO No Trim 21	SealTite PRO XTR	SealTite PRO HFO	A-Component
50	350	363	650	1975	775	550	2400	600
55	288	325	513	1825	700	500	1950	525
60	250	288	450	1625	588	390	1575	450
65	200	250	400	1438	488	355	1275	350
70	188	225	338	1225	425	310	1013	263
75	150	175	275	1050	325	250	800	213
80	125	150	213	800	263	205	600	175



## A-SIDE INFORMATION

<b>Gallons</b>	49	49	49	49	49	49	49
<b>Inches</b>	28	28	28	28	28	28	28
<b>Lbs</b>	500	500	500	500	500	500	500

## B-SIDE INFORMATION

<b>PRODUCT NAME</b>	<b>SealTite PRO Open Cell</b>	<b>SealTite PRO High Yield</b>	<b>SealTite PRO No Mix</b>	<b>SealTite PRO OCX</b>	<b>SealTite PRO No Trim 21</b>	<b>SealTite PRO XTR</b>	<b>SealTite PRO HFO</b>
<b>Gallons</b>	50.85	51.56	49.8	51.54	49.62	50.03	49
<b>Inches</b>	29.57	29.98	27.5	29.97	28.85	29.09	28
<b>Lbs</b>	475	475	460	500	475	460	500
<b>Viscosity, cps</b>	100 – 120	150 – 250	200 – 300	700 – 900	700-900	200 – 300	600 – 700
<b>Specific Gravity</b>	1.12	1.10	1.11	1.16	1.15	1.102	1.22
<b>Lbs/Gal</b>	9.185	9.213	9.224	9.701	9.63	9.194	10.174

## PROCESSING CONDITIONS

<b>PRODUCT NAME</b>	<b>SealTite PRO Open Cell</b>	<b>SealTite PRO High Yield</b>	<b>SealTite PRO No Mix</b>	<b>SealTite PRO OCX</b>	<b>SealTite PRO No Trim 21</b>	<b>SealTite PRO XTR</b>	<b>SealTite PRO HFO</b>
<b>Temp. Drums</b>	80°F – 90°F	80°F – 90°F	80°F – 90°F	80°F – 90°F	80°F – 90°F	80°F – 90°F	70°F – 80°F
<b>Temp. (A)</b>	115°F – 140°F	115°F – 140°F	120°F – 140°F	120°F – 140°F	115°F – 135°F	120°F – 140°F	105°F – 135°F
<b>Temp. (B)</b>	115°F – 140°F	115°F – 140°F	120°F – 140°F	120°F – 140°F	115°F – 135°F	120°F – 140°F	105°F – 135°F
<b>Temp. Hoses</b>	115°F – 140°F	115°F – 140°F	120°F – 140°F	120°F – 140°F	115°F – 135°F	120°F – 140°F	105°F – 135°F
<b>Pressure (psi)</b>	1,000 – 1,500	1,000 – 1,500	1,000 – 1,500	1,000 – 1,500	1,000 – 1,500	1,000 – 1,500	1,000 – 1,500
<b>Mix Chamber</b>	AR4242 01	AR4242 01	AR4242 01	AR4242 01	AR4242 01	AR4242 01	AR4242 01
<b>Lift Thickness (max)</b>	-	-	-	6"	6"	-	4" 3" + 2.5"