

# ULC Evaluation Report

## ULC ER-R39311

Issued Date: 2020-10-30

Visit UL's On-Line Certifications Directory:  
[www.ul.com/productiq](http://www.ul.com/productiq) for current status of report.

**UL Category Code: ULEX7**

**CSI MasterFormat®**

**DIVISION: 07 21 00 THERMAL INSULATION**  
**Sub Level : 07 21 19 – Foamed-In-Place Insulation**

### COMPANY:

**CARLISLE Spray Foam Insulation**  
2865 Argentia Rd, Unit #3  
Mississauga, ON. L5N 8G6 Canada  
[www.carlislefi.com](http://www.carlislefi.com)

[www.carlisesfi.com](http://www.carlisesfi.com)

### 1. SUBJECT

**SealTite ONE**

### 2. SCOPE OF EVALUATION

2015 National Building Code of Canada, NBCC (Sept. 28, 2018)

NBCC Division B, Part 5      Environmental Separation  
Sentence 5.9.1.1.(1)      Compliance with Applicable Standards

NBCC Division B, Part 9 – Housing and Small Buildings  
Article 9.25.2.2 Insulation Materials  
Article 9.25.2.5 Installation of Spray-Applied Polyurethane

The product was evaluated for the following properties:

- Physical Properties (CAN/ULC-S705.1-15)
- Surface Burning Characteristics (CAN/ULC S102)





**3.0 REFERENCED DOCUMENTS**

**CAN/ULC:**

- CAN/ULC-S102, Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies
- CAN/ULC-S705.1, Standard for Thermal Insulation, Spray Applied Rigid Polyurethane Foam, Medium Density – Material Specification
- CAN/ULC-S705.2:, Standard for Thermal Insulation, Spray Applied Rigid Polyurethane Foam, Medium Density – Application
- CAN/ULC-S774, Standard Laboratory Guide for the Determination of Volatile Organic Compound Emissions from Thermal Insulating Systems

**4.0. USES**

**Carlisle SealTite ONE**, spray-applied, rigid polyurethane medium density foam is intended for use as a building thermal insulation or for other purposes in building and non-building applications in both site-built construction and building prefabrication process.

This Report does not cover SealTite ONE for use in roofing applications, radon resistance systems, or fire resistive construction. Additional evaluations and testing required to meet these and other applications.

**5.0 PRODUCT DESCRIPTION**

The product is a spray applied, rigid polyurethane medium density foam. The site sprayed foam system consists of two components (isocyanate and resin). The two components are mixed on site by qualified installers with fixed-ratio positive displacement equipment and is applied at a minimum density of 37.9 kg/m<sup>3</sup> (2.37 pcf). The colour of the final product is Light Teal.

The product is manufactured at an ISO 9001:2015 registered facility and quality audited by UL were UL/ULC Field Engineering staff audit manufacturing facilities to verify continuing material quality compliance.

**6.0 PERFORMANCE CHARACTERISTICS**

The SealTite ONE thermal insulation was evaluated for the performance characteristics as reported below in Table 1 Performance Characteristics with testing in accordance with sections of the following test standards:

CAN/ULC S705.1-2015-Rev 1, Standard for Thermal Insulation, Spray Applied Rigid Polyurethane Foam, Medium Density – Material Specification

<b>Table 1: Performance Characteristics</b>		
Properties	Requirements	Results
Density (minimum site specified density)	≥ 28 kg/m <sup>3</sup>	37.9 kg/m <sup>3</sup>
Air Permeance	≤ 0.02 L/(s·m <sup>2</sup> )@75Pa	0.0003 L/(s·m <sup>2</sup> )@75Pa
Compression Strength	≥ 170 kPa	270 kPa
Dimensional Stability		
28 d at -20±3°C, ambient humidity	-2/+5%	+0.3%
28 d at 80±2°C, ambient humidity	-2/+8%	-0.1%
28 d at 70±2°C, 97±3% R.H	-2/+14%	+5.8%



Properties	Requirements	Results
Fungi Resistance	No Growth	No Growth
Long Term Thermal Resistance		
@ 50mm thickness	$\geq 1.80 \text{ m}^2\cdot\text{K}/\text{W}$	$1.80 \text{ m}^2\cdot\text{K}/\text{W}$
@ 75mm thickness	Declare	$2.73 \text{ m}^2\cdot\text{K}/\text{W}$
@ 100mm thickness	Declare	$3.73 \text{ m}^2\cdot\text{K}/\text{W}$
Open-Cell Content	$\leq 10\%$	3.0 %
Surface Burning Characteristics		
Flame Spread Rating	$\leq 500$	230
Tensile Strength	$\geq 200 \text{ kPa}$	237 kPa
Time to Occupancy	$\leq 30 \text{ Days}$	1 day
Water Absorption by Volume	$\leq 4.0 \%$	3.4%
Water Vapour Permeance @50mm thickness	$\leq 60 \text{ ng}/(\text{Pa}\cdot\text{s}\cdot\text{m}^2)$	$36 \text{ ng}/(\text{Pa}\cdot\text{s}\cdot\text{m}^2)$

## 7.0 INSTALLATION

Installation of the insulation must comply with this report and the manufacturer's published installation instructions. The manufacturer's published installation instructions are to be available at the jobsite at all times during installation.

- A. The specified minimum site density must comply with the above requirement, as measured on-site in accordance with CAN/ULC S705.2.
- B. Installation must be by a licensed installer in accordance with the manufacturer's directions and follow the CAN/ULC S705.2 requirements.
- C. The time to re-occupancy during retrofit construction is a minimum one day (24 hours).

## 8.0 CONDITIONS OF USE

The SealTite ONE material described in this Report has been evaluated in accordance with code sections listed in Section 2.0, subject to the following conditions:

- A. Materials and methods of installation must comply with this report and the manufacturer's published installation instructions. In the event of a conflict between the manufacturer's published installation instructions and this report, the manufacturer shall be consulted.
- B. This product is manufactured in Cartersville, GA, USA under UL's audit of quality elements.
- C. This product is combustible. Based on the flame spread, this product may require additional protection from fire.

## 9.0 SUPPORTING EVIDENCE

**CARLISLE** has submitted technical documentation for ULC's review. Testing was conducted at laboratories recognized as ISO 17025 compliant. The test data submitted for this product is summarized below.

- A. Sample Selection of SealTite ONE materials by an ISO 17025 accredited test lab.
- B. Data in accordance with CAN/ULC S705.1. Compliant test report from an ISO 17025 accredited test lab.
- C. CAN/ULC-S774 VOC test report by an ISO 17025 accredited test lab.
- D. Human health Risk Assessment of Volatile Organic Compound by a Diplomate of the Board of Toxicology (DABT) (PHD).
- E. Caliber Quality Solutions Inc. (Certification Organization / SQAP / site inspections).



## **10.0 IDENTIFICATION**

SealTite ONE thermal insulation described in this evaluation report is identified by a marking bearing the report holder's name (**CARLISLE**) and the evaluation report number **ULC ER-R39311**. The validity of the evaluation report is contingent upon this identification appearing on the product drums.

## **11.0 CLIENT LOCATIONS / CONTACT**

CARLISLE Spray Foam Insulation  
2865 Argentia Rd, Unit #3  
Mississauga, ON. L5N 8G6 Canada

905-826-4851  
[www.carlislefi.com](http://www.carlislefi.com)

## **12.0 USE OF UL EVALUATION REPORT**

**12.1** The approval of building products, materials or systems is under the responsibility of the applicable authorities having jurisdiction.

**12.2** ULC Evaluation Reports shall not be used in any manner that implies an endorsement of the product, material or system by ULC.

**12.3** The current status of this report, as well as a complete directory of UL Evaluation Reports may be found at [UL.com](http://UL.com) via our [Product iQ™ database](#).

**[www.ul.com/productiq](http://www.ul.com/productiq)**

© 2020 ULC Inc.

*This ULC Evaluation Report is not an endorsement or recommendation for use of the subject and/or product described herein. This report is not the UL Listing or UL Classification Report that covers the subject product. The subject product's UL Listing or UL Classification is covered under a separate UL Report. UL disclaims all representations and warranties whether express or implied, with respect to this report and the subject or product described herein. Contents of this report may be based on data that has been generated by laboratories other than UL that are accredited as complying with ISO/IEC Standard 17025 by the International Accreditation Service (IAS) or by any other accreditation body that is a signatory to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA). The scope of the laboratory's accreditation shall include the specific type of testing covered in the test report. As the accuracy of any non-UL data is the responsibility of the accredited laboratory, UL does not accept responsibility for the accuracy of this data.*